

## FloorBridge® Connect 13

### Elastic 2K hybrid adhesive

#### Properties

- Hardening within 1 hour
- High flexibility
- Quick initial adhesion
- Odourless
- Non-classified

#### Application areas

For bonding the rubber insert for FloorBridge® CPS-joint profiles.

#### Product data

Colour shade: Grey  
Container size: 500 g double cartridge

#### Technical data

Film-forming time: Approx. 10-12 minutes (20°C, 50% RH)  
Hardening: Approx. 60 minutes (20°C, 50% RH)  
Solid content: 100%  
Mixing ratio (volume): 1:1  
Thickness: 1.41 g/l  
Shore hardness (DN 53505): 45  
Tensile shear strength (DIN 53504):  
Approx. 1.5 N/mm<sup>2</sup>  
Tensile strength (DIN 53501): Approx. 2.4 N/mm<sup>2</sup>  
Elongation/Elasticity (DIN 53504): Approx. 400%  
Module at 100% elongation (ISO 8339): Approx. 1.4 N/mm<sup>2</sup>  
Volume change: Approx. 3%

#### Consumption:

Ca. one 2K cartridge for 5 meters bonding expansion insert (CPS-profile).



#### Resistance

- Good UV stability and resistance to weathering and ageing
- Temperature resistant from -40°C to +90°C
- Generally very high resistance:

Water	Very good resistance
Salt water	Very good resistance
Aliphatic solvent	Very good resistance
Oils and greases	Very good resistance
Diluted inorganic acids and bases	Very good resistance
Ester	Temporary resistance
Ketones	Temporary resistance
Aromatic hydrocarbons	Temporary resistance
Concentrated acids	No long-term resistance
Chlorinated hydrocarbons	No long-term resistance

#### Storage conditions / Shelf life:

12 months in the original packaging when stored in a cool, dry and UV-protected place.

### Substrate condition/Pre-treatment

The adhesive surfaces must be cleaned and any contaminants such as release agents, preservatives, grease, oil, dust, water, old adhesives/sealants as well as any other substances that could impair adhesion must be removed. Before the rubber insert is bonded to the FloorBridge® joint profiles, it must be cleaned with FloorBridge® Cleaner 12 (see FloorBridge Cleaner 12 product data sheet).

### Application conditions/Limits:

Material temperature: +5°C to +40°C  
Ambient temperature: +5°C to +40°C

### Application instructions:

Processing time (ISO 10563): Approx. 10 minutes (20°C, 50% RH)  
Hardening time (ISO 10563): Approx. 60 minutes (20°C, 50% RH)

Easy handling with conventional 2K cartridge gun or compressed air. Strict adherence to the mixing ratio (1:1) is required to prevent irregularities in the hardened product. This can only be ensured with static mixers.

### Application notes:

The inclusion of air must be avoided to achieve optimal adhesion and good mechanical properties. The time until hardening can be shortened by addition of moisture and exposure to higher temperatures. During the summer months, the substrate temperature of the parts that will be bonded must be taken into account. Temperatures >40°C during processing can have a negative effect on the material properties. During processing, the rubber insert must be bonded before the FloorBridge® Connect 13 film-forming time.

If the products are stored and/or transported at high temperatures/humidity for long periods of time (several weeks), a reduction in the shelf life or a change in the material properties cannot be ruled out.

### Legal notes

The information and, in particular, the recommendations relating to the application and use of FloorBridge® products, are given in good faith based on the current knowledge and experience of FloorBridge® International GmbH about the products and apply if properly stored, handled and under normal conditions in accordance with FloorBridge® International GmbH recommendations. In practice, the differences in materials, substrates and deviating working conditions are so substantial that FloorBridge® International GmbH shall neither accept any warranty nor liability for a particular merchantability or suitability for a particular purpose, neither derived from this information nor from a written recommendation or any other advice offered. The user of the product must verify the product's suitability for the intended purpose of use. FloorBridge® International GmbH reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted by FloorBridge® International GmbH subject to final confirmation and subject to the current terms and conditions regarding sales and deliveries of FloorBridge® International GmbH. Users must always refer to the most recent issue of the local product data sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of FloorBridge® International GmbH.