

## FloorBridge® Connect 04

2-part epoxy resin-based composite adhesive, very low emission

### Areas of Application

As an adhesive and mortar for force-fitted connection of old and new concrete with FloorBridge® joint profiles.

### Advantages

- physiologically harmless after curing
- very good wetting
- very good shear-/adhesive strength
- high mechanical strength
- high abrasion and impact strength
- easy workability and miscibility

### Product Data

<b>Colours</b>	Part. A:	white
	Part. B:	dark grey
	Part. A+B mixed:	grey
<b>Packaging</b>		Unit 26 kg
	Part. A:	20 kg
	Part. B:	6 kg
	Pallet unit:	728 kg = 28 units à 26 kg (28 x 20 kg part. A and 28 x 6 kg part. B) = 1 pallet

**Approval** CE-certified EN 1504-4

### Technical Data

**Chemical Base** Epoxy resin

**Density (+23°C)** approx. 1,6 kg / litre (Part. A+B, mixed)

**Layer Thickness** max. 5 mm per operation

For higher layer thickness apply in several layers. When using multiple units, mix and use completely one unit after the other. Do not mix the following unit until the previous one has been fully used in order to avoid a reduction in pot life and application time.



### Mechanical / Physical Properties

**Compressive Strength (DIN EN ISO 604)** approx. 55 N/mm<sup>2</sup> (14 days / +23°C)

### Application Details

In addition to the product data sheet, please note the respective instructions in the FloorBridge® installation manual.

### Consumption / Dosage

1,6 kg/m<sup>2</sup> per mm of thickness

### Substrate Conditions

The substrate must be sufficiently stable (compressive strength min. 25 N / mm<sup>2</sup>). The substrate must be level, fine-grained, solid, dust free, dry, free of grease, oil and other contaminants and free of loose and sanding parts. The pull-out strength must not be less than 1.5 N / mm<sup>2</sup>. If necessary, the substrate must also be dried (residual moisture in concrete is max. 4 %).

### Application Conditions / Limitations

<b>Substrate Temperature</b>	+ 10°C to +25°C
<b>Ambient Temperature</b>	+ 10°C to +25°C
<b>Material Temperature</b>	+ 10°C to +25°C
<b>Dew Point</b>	

Observe dew point, exclude condensation!

Substrate temperature during application must be at least +3°C above dew point.

### Application Instructions

#### Mixing

Part A : part B = 100 : 30 by weight (3,33 : 1)

Mix with electric mixer for at least 2 minutes until it becomes a homogeneous colour mixture, streak-free. Mix at low speed (300 – 400 rpm) to avoid air inclusions while mixing. Then, empty the entire mix into a clean container and mix again for approx. 1 more minute.

Mix only that quantity of FloorBridge® Connect 04 which can be used within its pot life.

#### Application Method / Tools

When applying the adhesive in a thin layer, apply the mixed adhesive to the prepared substrate with a spatula, trowel, notched trowel etc. Before, during and after coating, attention must be paid to the dew point distance (+3°C).

#### Cleaning of Tools

Clean all tools and application equipment immediately after use with commercial epoxy resin cleaner. Hardened / cured material can only be mechanically removed.

#### Pot life

At +23°C approx. 45 minutes

The pot life begins when the resin and hardener mixing starts. When mixing larger quantities there is a higher heat of reaction which shortens the pot life.

#### Value Base

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

### Curing Conditions

#### Notes

The FloorBridge® resin is formulated to have low creep under permanent loading. However due to the creep behaviour of all polymer materials under load, the long-term structural design load must account for creep. Generally, the long-term structural design load must be lower than 20-25 % of the failure load. In this case additional safety factors do not need to be considered. Exposure to UV-radiation leads to colour change. If FloorBridge® Connect 04 is to be reworked with a suitable coating material, the freshly applied adhesive must be sprinkled with quartz sand.

### Safety Information

#### Important Safety Information

For detailed information refer to the most recent Safety Data Sheet at [www.floorbridge.com](http://www.floorbridge.com).

#### Storage conditions / Shelf Life

12 months from date of production if stored properly in original, unopened, sealed and undamaged packaging, in dry conditions at temperatures between +10°C and +25°C. Protect from direct sunshine.

### Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of FloorBridge® products, are given in good faith based on the current knowledge and experience of FloorBridge® International GmbH about the products, and apply if properly stored, handled and under normal conditions in accordance with FloorBridge® International GmbH recommendations.

In practice, the differences in materials, substrates and deviating working conditions are so substantial, that FloorBridge® International GmbH shall neither accept any warranty nor liability for a particular merchantability or suitability for a particular purpose, neither derived from this information nor from a written recommendation or any other advice offered. The user of the product must verify the product's suitability for the intended purpose of use.

FloorBridge® International GmbH reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to final confirmation and subject to our current terms and conditions regarding sales and deliveries.

Users must always refer to the most recent issue of the local product data sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of FloorBridge® International GmbH.