



## FloorBridge® Connect 20 TK

PMMA based compound adhesive for freezing areas

### Application

Adhesive and adhesive mortar for friction-locked connections of and in old concrete and new concrete with FloorBridge® joint profiles.

### Advantages

- easier workability, easier mixing
- quick hardening
- excellent adhesion on various surfaces
- good hydrolysis resistance
- high mechanical strength
- solvent-free

### Product Data

<b>Colour shade base compound (Connect 20)</b>	grey
<b>Catalyst liquid (Connect 20 liquid catalyst)</b>	crème-white
<b>Mixed</b>	grey
<b>Delivery size</b>	Container 10 kg Liquid catalyst: 0,44 l (45 x 10 kg base compound = 1 Pal)
<b>Approval</b>	CE mark in accordance with EN 1504-3

### Technical Data

<b>Chemical basis</b>	Polymethylmethacrylate
<b>Density (23°C)</b>	approx. 1.5 kg/l (mixed)
<b>Coating thickness</b>	max. 5 mm per application

Greater coating thicknesses require multiple applications. To prevent shortening the workability time, individual containers should be used up and never mixed with freshly prepared material.

<b>Consumption / Dosing</b>	1,5 kg/m <sup>2</sup> per mm layer-thickness – ca. 6 kg/meter joint profile
-----------------------------	--



### Mechanical/physical properties

#### Compressive strength

Curing time*	
<b>3 hours</b>	<b>50 N/mm<sup>2</sup></b>
<b>24 hours</b>	<b>60 N/mm<sup>2</sup></b>
<b>7 days</b>	<b>60 N/mm<sup>2</sup></b>

\*Catalyst addition depending on temperature application range – see table catalyst dosing.

#### Adhesive tensile strength

At 20°C: on concrete dry: > 2 N/mm<sup>2</sup> (demolished concrete)

#### Application notes

In addition to this product data sheet, please observe the relevant notices in the FloorBridge® installation manual.

### Substrate condition

The substrate must have sufficient load capacity (compressive strength at least 40 N/mm<sup>2</sup>). The surface must be level, fine textured, stable, dust-free, dry, grease and oil free and free from loose and sanding particles. The tear strength must be at least 1.5 N/mm<sup>2</sup>. If necessary, the substrate must be dried. The surface to be coated must be dry and free from ice. The surface must remain dry until it has hardened. (Remaining moisture for concrete max 6%). If the substrate requires re-profiling, we recommend PMMA or epoxy mortar with a compressive strength of at least 40 N/mm<sup>2</sup>. For example, we recommend epoxy-based product FloorBridge® epoxy mortar 300. Carry out preliminary tests.

### Application conditions/limits

<b>Substrate temperature</b>	--25°C to – 10°C
<b>Ambient temperature</b>	-25°C to - 5°C
<b>Material temperature</b>	-5°C to +5°C

Catalyst dosing according to table.

The composite adhesive is mixed in the deep-freeze area.

### Dew point

Observe the dew point and exclude condensation! The substrate temperature during the application must be at least +3°C above the dew point temperature.

The relative humidity must be < 90%.

### Application instructions

The reaction times will shorten with increasing temperatures and higher catalyst ratios, and vice versa accordingly. The following table indicates the recommended catalyst quantity to adapt the hardening reaction to the temperature.

	<b>Catalyst dosing FloorBridge® liquid catalyst 20</b>
<b>Underground temperature in °C</b>	-25 bis -10
<b>Liquid catalyst in %</b>	4

During the curing phase, care must be taken to ensure that no cold draughts blow across the surface of the composite adhesive.

### Application method and devices

Recommended mixer with Dippel blade mixing head. To apply a thin adhesive coating, apply the mixture to the pre-treated substrate with a putty knife, trowel, etc. Observe the dew point gap (+3°C) before, during and after coating.

### Mixing

To start, mix the contents of the bucket thoroughly.

Then slowly add the catalyst to the running mixer and mix for 2 minutes.

Make sure the material on the bottom and the edge of the container is included.

The composite adhesive must not be stored at temperatures below -5°C and should be mixed in the freezer compartment, as otherwise the pot life will be reduced.

Ideally, store between -5°C and +5°C; transport the material to the joint, open it immediately and mix it without storing it for long periods in the freezer, so that the material does not cool down too much. This ensures a pot life of approx. 25 minutes.

### Device cleaning

All tools and application devices must be cleaned immediately after use with a conventional cleaner for PMMA. (e.g.: ethyl acetate) Hardened material can only be removed mechanically.

### Potlife

At -25°C and 4% catalyst: approx. 25 mins.

The pot life begins when mixing. The material must be cooled to a temperature between -5°C and +5°C prior to adding the catalyst and for application. Mixing larger quantities generates more heat of reaction. This shortens the pot life.

### Bonding SM sealing tape / wall connection rubber

When bonding SM sealing tape, ensure that the tape (except for the expansion zone) is fully covered on both sides. (This is particularly important in the upward pull area).

When bonding the wall connection rubber with Connect 20, a wall panel must be bonded immediately after bonding as protection.

### Rainproof

after approx. 45 minutes.

### Grinding/walkable:

after approx. 60 minutes

### Drivable over:

after appr. 3 hours

### Sealing

The joint profile and the existing adhesive coating between profile and concrete can be sealed after grinding. Products on binder base PMMA (FloorBridge®), polyaspartic, epoxy and PU are suitable. However, tests before are recommended.

### Further notes

All values listed on the technical data sheet are based on laboratory trials. In practice, the values may deviate due to various influences.

### Curing conditions

#### Notes

The FloorBridge® compound adhesive was formulated to have the least possible creeping under continuous loads. Due to the creep behaviour, which all polymers have under loads, creeping must be taken into account when calculating the permissible load. The constant actual load on the bonding must never exceed 20-25% of the breaking load. No additional safety factors must be considered in this case. Exposure to UV radiation causes the colour to change.

### Safety regulations

#### Important safety notes

For detailed information, please consult the current safety data sheet at [www.floorbridge.com](http://www.floorbridge.com)

### Storage conditions / shelf life

12 months in unopened containers from the date of production. The products must be stored in a cool, dry, frost-free, and airtight container. The composite adhesive must be brought to a temperature of at least 10°C before use. Direct sunlight on the containers should also be avoided on the construction site. After partial removal, reseal the containers airtight!

### Legal Notes

The information and, in particular, the recommendations relating to the application and use of FloorBridge® products, are given in good faith based on the current knowledge and experience of FloorBridge® International GmbH about the products and apply if properly stored, handled and under normal conditions in accordance with FloorBridge® International GmbH recommendations. In practice, the differences in materials, substrates and deviating working conditions are so substantial that FloorBridge® International GmbH shall neither accept any warranty nor liability for a particular merchantability or suitability for a particular purpose, neither derived from this information nor from a written recommendation or any other advice offered. The user of the product must verify the product's suitability for the intended purpose of use. FloorBridge® International GmbH reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted by FloorBridge® International GmbH subject to final confirmation and subject to the current terms and conditions regarding sales and deliveries of FloorBridge® International GmbH. Users must always refer to the most recent issue of the local product data sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of FloorBridge® International GmbH.